

6061 O Aluminum Sheet

[Request more information](#)

Properties

General

Property	Temperature	Value	Comment
Density	23.0 °C	2.7 g/cm³	Typical for Wrought 6000 Series Aluminium

Mechanical

Property	Temperature	Value	Comment
Elastic modulus	23.0 °C	70 GPa	Typical for Wrought 6000 Series Aluminium
Elongation	23.0 °C	16 %	
Plane-Strain Fracture Toughnes	23.0 °C	22 - 35 MPa·√m	Typical for Wrought 6000 Series Aluminium
Poisson's ratio	23.0 °C	0.33 [-]	Typical for Wrought 6000 Series Aluminium
Shear modulus	23.0 °C	26 - 26.5 GPa	Typical for Wrought 6000 Series Aluminium
Tensile strength	23.0 °C	147 MPa	

Yield strength 23.0 °C

[108 MPa](#)

Thermal

Property	Temperature	Value	Comment
Coefficient of thermal expansion	23.0 °C	1.6E-5 - 2.4E-5 1/K	Typical for Wrought 6000 Series Aluminium
Melting point		555 - 655 °C	Typical for Wrought 6000 Series Aluminium
Specific heat capacity	23.0 °C	887 - 963 J/(kg·K)	Typical for Wrought 6000 Series Aluminium
Thermal conductivity	23.0 °C	170 - 220 W/(m·K)	Typical for Wrought 6000 Series Aluminium

Electrical

Property	Temperature	Value	Comment
Electrical conductivity	23.0 °C	2.10E+7 - 3.40E+7 S/m	Typical for Wrought 6000 Series Aluminium
Electrical resistivity	23.0 °C	2.9E-8 - 5E-8 Ω·m	Typical for Wrought 6000 Series Aluminium

Technological properties

Property	
Processing history	○
Workability	Excellent workability.